

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
31 March 2005 (31.03.2005)

PCT

(10) International Publication Number
WO 2005/028580 A2

(51) International Patent Classification⁷:

C09J

(21) International Application Number:

PCT/US2004/024355

(22) International Filing Date: 29 July 2004 (29.07.2004)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

60/490,841

29 July 2003 (29.07.2003) US

(71) Applicant (*for all designated States except US*):
NU-CHEM, INC. [US/US]; 2200 Cassens Drive, Fenton,
MO 63026 (US).

(72) Inventor; and

(75) Inventor/Applicant (*for US only*): TAYLOR, Edward,
W. [US/US]; 181 Tortuna Drive, Ballwin, MO 63021 (US).

(74) Agent: POLSTER, J., Philip; Polster, Lieder, Woodruff
& Lucchesi, L.C., 12412 Powerscourt Drive, Suite 200, St.
Louis, MO 63131 (US).

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— *without international search report and to be republished upon receipt of that report*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: WATERBORNE COATINGS AND FOAMS AND METHODS OF FORMING THEM

(57) Abstract: Methods of forming epoxy-based foams include reacting at least one sulfonyl hydrazide chemical blowing agent with at least one curing agent at a temperature between 1°C and about 60°C. Illustratively, the curing agent is an emulsion of an adduct of a polyamine. A low density ambient cured, non-exothermic, closed cell epoxy foam may be formed for use as an insulation. This insulation may be fire retardant or fire resistant. The foam may be applied as a liquid material which then foams under ambient temperatures and pressures, or as a panel which has been pre-cast, and delivered in a slab form. Densities as low as 0.24 g/cm³ (15 lbs./ft³) can be achieved at 24°C with compressive strengths approaching 1500 psi.

WO 2005/028580 A2